



## PRODUCT DATA SHEET

# ANDEROL FGCS-2 PLUS



Synthetic Food Grade Calcium Sulfonate Complex Grease NLGI-2

### ADVANTAGES/BENEFITS

- Superior mechanical stability, particularly in the presence of heat and water
- Formulated to resist separation under centrifugal forces
- Excellent rust prevention properties
- Excellent load carrying ability and wear protection
- Excellent resistance to water washout and spray-off
- H1 grease for incidental contact with food
- Heavy duty food-grade applications
- Life performance is typically increased by two to three that of a regular mineral oil based grease

### APPROVAL

ANDEROL® lubricants are approved, recommended and field tested by many OEM's in the food processing, bottling, canning, meat processing, and pharmaceutical industries.

### HANDLING & STORAGE

ANDEROL® lubricants generally present little hazard in normal handling if ordinary care is exercised. If spilled, cover with inert, absorbent material and remove. Flush the area with water.

Although ANDEROL® lubricants are not highly flammable, they will burn and should be kept away from open flames. In case of fire, use water spray, foam, carbon dioxide, or dry chemical.

ANDEROL® lubricants should be stored preferably in protected locations to prevent contamination. Do not re-use drums; flush and send to re-conditioner.

ANDEROL FGCS-2 PLUS is an over-based Calcium Sulfonate based grease with exceptional load carrying ability, excellent mechanical stability and good resistance to oxidation and corrosion.

ANDEROL FGCS-2 PLUS equals or outperforms other premium Food-Grade greases.

ANDEROL FGCS-2 PLUS has a NSF/H1 registration, and meets the lubrication requirements of equipment operating in food processing plants. This product is certified Kosher by the Orthodox Union and Halal by the Islamic Food Council of Europe.

PROPERTIES	TEST METHOD	ANDEROL FGCS-2 PLUS
Color	visual	Tan
Thickener		Ca-Sulfonate
Type of Base Oil		PAO
Operating temperature for long-term lubrication	ASTM D-2265	-40 to +177°C
Short time admissible temperature peak value	ASTM D-92	+200°C
Dropping Point	ASTM D-97	318°C
Worked Penetration	DIN ISO 2137	265 to 295 0.1 mm
Base Oil Viscosity @ 40°C	ASTM D-445	Approx. 50 mm <sup>2</sup> /s
4-Ball test welding load	ASTM D-2596	4000 N
Water Washout, % lost @ 80°C	ASTM D-1264	0.5
Bearing Life Performance, hours @ 1000 rpm, 160°C	ASTM D-3527	280
Low Temperature Torque at -40°C	ASTM D-4693	4.0 Nm
Designation	DIN 51.502	KPHC2R-40

FOR MORE INFORMATION PLEASE REFER TO THE RELEVANT MATERIAL SAFETY DATA SHEET

### REGISTRATIONS



This information is furnished without warranty, representation, inducement, or license of any kind except that it is accurate to the best of OUR knowledge or obtained from sources believed by ANDEROL® to be accurate. ANDEROL® does not assume any legal responsibility for use of reliance upon it. Only Chemists or chemically qualified lab technicians should carry out tests. Before using any chemicals, read its label and Material Safety Data Sheet.

**ANDEROL®**  
Specialty Lubricants

Groot Egtenrayseweg 23, 5928 PA Venlo, The Netherlands • Tel: +31 (0)77 3960340 • www.anderol-europe.com