

Lubricant Additives Business

Anderol[®] 465

Anderol[®] Industrial lubricants gears and bearings

Description

Synthetic Lubrication Oil

Anderol[®] **465** is an ISO Grade 68 (nominal), synthetic-di-ester based lubricant that is formulated to offer extended lubrication over a wide temperature range, resist gumming and speed fluctuations and to minimize wear.

Features and Benefits

- Excellent oxidation resistance.
- Reduces friction for low-wear rates.
- Good load carrying.
- Nominal operating temperature range -35° F to 270° F (-35°C to 130°C)
- Excellent corrosion and rust protection.

Compatibility

The following seals, paints and plastics are recommended for use in contact with **Anderol**[®] synthetic lubricants. Materials not recommended are also shown. For more information on other materials see our 'Compatibility Guide'.

RECOMMENDED:

Viton, High Nitrile Buna N, Teflon, Epoxy Paint, Oil-Resistant Alkyd, Nylon, Delrin, Celcon, PBT

NOT RECOMMENDED:

Neoprene, SBR Rubber, Low Nitrile Buna N, Acrylic Paint, Lacquer, Polystyrene, PVC, ABS

Application

- Impregnating fluid for sintered metal bearings, parts & wicks
- · Measuring and dispensing pumps and meters
- · Mechanical spring and actuator mechanisms
- · General-purpose medium viscosity lubricating oil
- · Office, computing and accounting machinery
- · Anti-friction bearings

Page 1 of 3 Edition: 2021-01-21



Lubricant Additives Business

Anderol[®] 465

Anderol[®] Industrial lubricants gears and bearings

Technical data*

PROPERTY	METHOD	ANDEROL 465
ISO VG	ASTM D-2422	68
SAE Viscosity Grade	SAE J 300	30
Viscosity @ 40°C, cSt	ASTM D-445	62.1
Viscosity @ 100°C, cSt	ASTM D-445	11.4
Viscosity Index	ASTM D-2270	180
Flash Point, °C	ASTM D-92	246
Pour Point, °C	ASTM D-97	-54
Evaporation, 22 hrs @ 100°C, (210° F) %	ASTM D-972	0.8
Evaporation, 6.5 hrs @ 204°C, (400° F) %	ASTM D-972	4
4-Ball Wear, 1200 rpm@ 75°C (167°F), 40 kg, 1 hr, mm	ASTM D-4172	0.8
4-Ball EP, Weld Point, kg	ASTM D-2783	100
Density, lbs/gallon	ASTM D-1250	7.66
Viscosity 100 °F, SUS	ASTM D-2161	317
Viscosity 210 °F, SUS	ASTM D-2161	65.2
Viscosity -20 °F(-29°C), cSt	ASTM D-445	8000
Copper Strip Corrosion, 24 hrs @ 212° F (100°C)	ASTM D-130	1a

*The analytical data are guide values.

Page 2 of 3 Edition: 2021-01-21



Lubricant Additives Business

Anderol[®] 465 Anderol[®] Industrial lubricants gears and bearings

Consult safety data sheet (SDS) for additional handling information on **Anderol**[®] **465** For registrations, certificates and approvals please refer to anderol.com

R = registered trade mark

This is a product of Anderol BV Groot Egtenrayseweg 23 5928PA VenIo The Netherlands www.anderol.com

This information and our technical advice – whether verbal, in writing or by way of trials – is subject to change without notice and given in good faith but without warranty or guarantee, express or implied, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

©2021 LANXESS and the LANXESS Logo are trademarks of LANXESS Deutschland GmbH or its affiliates. All trademarks are registered in many countries in the world.

North America +1.833.LANXESS customer.care@lanxess.com Europe, Middle East & Africa +31.77.396.0340 customerservice@anderol.com South & Central America +55.19.3522.5083 atendimento.cliente@lanxess.com Asia Pacific +86.21.6109.6666 Orders.apac@lanxess.com

Page 3 of 3 Edition: 2021-01-21

